

PROMATECT®-S E&M Services Enclosure



Promat

Introduction

Electrical and mechanical (E&M) services require fire protection for the following reasons:

- To maintain function of certain essential electrical and/or mechanical systems and services,
- To prevent fire, smoke and toxic fume propagation from one building compartment to another.

It is necessary to ensure the continued function of essential electrical systems and services is maintained during fire, for a specified period of time, until all the building occupants have escaped. Electrical systems that need protection from fire may include:

- · Electrical operated fire alarms,
- Emergency escape route lighting,
- · Electrical operated extinguishing systems,
- · Smoke extraction vent systems,
- Power supply for fire service elevators in high-rise buildings,
- Water mains supply and pumps servicing sprinkler systems,
- Essential life support and/or computer, communication or information technology networks.

It is worth noting that most electrical services and to some extent mechanical services have a high component of plastic materials such as polyvinylchloride, polypropylene, polyethylene, synthetic rubbers etc. The risks associated with these combustible plastics are such that fire can and will spread or propagate through the services. Intensive combustion also means that plastics frequently release toxic and corrosive fumes that can include particulates, unburned fuel, carbon dioxide and carbon monoxide which are not only harmful to the building and its contents but also to its occupants. Such fires can also cause the following problems:

- Production of corrosive and extremely toxic gases,
- Long term destruction of construction and related equipment,
- Smoke development and toxic gases in corridors and escape routes,
- Difficult evacuation.
- Impede fire rescue activities by fire fighters.

Reliability Of Fire Resistant Cables

Typical uses of cables to, in and from Electrical and Mechanical enclosures include fire alarms, emergency lighting, addressable alarm systems, CCTV systems, emergency power supplies and smoke and fire shutters. These cables are normally designed to meet the standards for Fire Detection and Alarm Systems in BS5839: Part 1 and Codes of Practice for Emergency Lighting in BS5266: Part 1.

Most fire resistant cables have been subjected to tests in accordance with BS6387: 1994 "Specification for performance requirements for cables required to maintain circuit integrity under fire conditions" and/or IEC60331-11, 21, 23 & 25 "Test for electric cables under fire conditions – circuit integrity".



Unfortunately, these standards only test single cables, without any support system, exposed to a small gas flame by means of an elongated Bunsen burner. The heat applied during the test is localised to a small area. While such a test may be adequate for small cables carefully secured directly to a fire resisting wall or floor, it is arguably not suitable to assess the fire performance of larger cables or bunches of cables, exposed to a fully developed fire on all sides, particularly if they are supported on a suspended cable tray which may pass through compartment walls or floors.

Although the cables may achieve the highest classification of the standard, they may not survive as expected if they are exposed on all sides to a fully developed fire, for example, the ISO834 time-temperature fire curve.

Fire Resistance Test Standards For Cable Protection Systems

The German standards DIN4102, "Fire behaviour of building materials and building components", Parts 11 and 12 specify fire resistance test for cable protection systems that simulate a fully developed fire scenario.

DIN 4102: Part 11 assesses the encasement system when exposed to a fully developed internal fire. The integrity of the encasement, and any penetrations through walls and floors, is measured, as well as the temperature on the outer surface of the duct (140°C mean rise, 180°C maximum rise). The heating curve for DIN 4102: Part 11 is the same as that used in BS476: Part 20 and AS1530: Part 4 and the failure criteria for integrity and insulation are identical. The systems detailed herein have been successfully tested and assessed and are approved for use to provide a performance in accordance with BS476: Part 20 and AS1530: Part 4 in terms of compartmentation.

DIN 4102 Part 12 assesses the encasement system when exposed to a fully developed external fire. In addition to the requirement to maintain the integrity of the encasement and any penetrations through walls or floors, the standard requires that:

- (a) The cables continue to function for the duration of the exposure period,
- (b) The temperature on the cable jacket should not exceed 150°C.

The tested encasement system protects a wide range of different cable types. Power is passed through the cables throughout the test. As an added safety factor, the system will ensure that the temperature on the cable jacket does not exceed 120°C.

The Australian/New Zealand standard AS/NZS 3013 "Electrical installations – Classification of the fire and mechanical performance of wiring systems" describes the level of protection of a wiring system against fire and/or accidental mechanical damage. The tests methods described within this standard call for wiring systems to maintain circuit integrity when subjected to fire test, mechanical damage tests, and fire and water tests. The resistance to fire test is to determine the ability of a wiring system to maintain circuit integrity under fire conditions for a specified period of time of up to 120 minutes. The wiring system shall be tested in a horizontal furnace complying with AS1530: Part 4, which also employs the ISO834 heating conditions.

Mechanical damage tests are to determine the degree of mechanical impact and cutting load to which the wiring system can be subjected without losing its circuit integrity. The tests are carried out separately from the fire test.

Fire and water tests assess the ability of a wiring system in maintaining its circuit integrity when subjected to fire conditions followed by hosing with water.

DIN 4102: Part 12 and AS/NZS 3013 are designed to test the functionality of cables under fully exposed fire conditions, unlike the IEC60331 test regime. The systems detailed herein relate to maintaining compartmentation only and should not be used where full function of the cables is to be maintained. For such systems compliant with DIN 4102: Part 12 and AS/NZS 3013, please consult Promat.

General Design Considerations

In the event of fire performance to internal and external fire, it has been established that an enclosure fabricated from fire resistant boards is one of the best solutions. Such systems have been tested successfully with ducts constructed from fire protective boards such as PROMATECT®-H, PROMATECT®-L or PROMATECT®-L500. These well established board systems are the only systems which currently fulfil all performance requirements, especially to the DIN4102 standards.

A suitably designed duct will:

- Prevent the propagation of fire from one building compartment to another,
- Assist in maintaining escape routes,
- Ensure the continuing operation of other services within a common service shaft.
- Reduce damage to localised area,
- Contain smoke and toxic fumes from burning cables.
- Ensure cable maintain their function when exposed to a fully developed fire.

Following are some of the factors to consider when determining the correct specification to ensure the enclosure system provides the required fire performance. Further advice can be obtained from the Promat Technical Department.

1. Required Fire Exposure

The specification of the enclosure system will depend on whether it is expected to resist external fire or internal fire or both.

2. Required Fire Performance

Generally, the most onerous requirement is to maintain the functional integrity of the circuit(s) when the system is exposed to external fire. If this is not needed, the performance requirements may be reduced by the approval authority to provide only stability, integrity and insulation of the enclosure system and/or wall and floor penetrations. On some occasions, further relaxations may be approved, e.g. a reduced insulation performance can sometimes be acceptable if no combustible materials or personnel are likely to be in contact with the duct.

3. Supporting Structure

The supporting hangers and their fixings should be capable of bearing the load of the complete enclosure system including any applied insulation material or other services suspended from it. Chemical anchors are generally not suitable. It is usually not advisable to employ unprotected hangers if the stress exceeds 6N/mm² for up to 240 minutes fire exposure and 10N/mm² for up to 120 minutes fire exposure and/or if the hanger lengths exceed 2m. The hanger centres should not exceed the distance limits given for the relevant Promat system.

4. Penetrations Through Walls & Floors

Care should be taken to ensure that movement of the cable system in ambient or in fire conditions does not adversely affect the performance of the wall, partition or floor or any penetration seal.

5. Ventilation Openings

Heat is generated as current flows through cable core conductors. The greater the electrical flow, the hotter the conductor will get. Excessive current flow will cause overheating and may result in overload, short circuit or ground fault. The material of the cable sheath, usually made from material such as PVC, polyurethane or polyethylene, usually has a self-ignition temperature between 340°C to 490°C.

In general, the heat generated by cables is negligible. However, a ventilation opening at appropriate intervals is recommended along a cable duct to prevent the build up of excessive heat. Ventilation openings must have a self-enclosing capability in the event of fire so as to prevent fire spread via such openings.

6. Access Hatches

For future inspection and installation of cables, a loose lid construction can be considered. Alternatively, the lid can be fixed and the inspection openings with hatches can be provided in the side walls of the duct. The hatch is secured completely to the duct using threaded inserts such as "Tecserts" (Armstrong Fastening Systems) at maximum 200mm centres.

7. Selection of Board Type

The Promat system can be based on PROMATECT®-H, PROMATECT®-L or PROMATECT®-L500. PROMATECT®-L or PROMATECT®-L500 are lighter than PROMATECT®-H and would probably be used in most applications. PROMATECT®-H offers a particularly robust system which is also highly resistant to impact and abrasion. Although both products are water tolerant, PROMATECT®-S would generally be preferred for more onerous conditions.

For tunnel environments and higher performance requirements, please consult Promat Technical Department.

8. Other Requirements

Acoustic performance, thermal insulation, water tolerance, strength and appearance can also be important considerations (see BS8313: 1997 Code of practice for accommodation of building services in ducts).

Fibre Optics

Fibre optic cables have a lower failure temperature due to the fact that the conductor is made of bundles of optical fibres that can be as thin as a human hair. Fibre optic cables are widely used for IT networking in many industries, especially in financial and healthcare services. For example, large banks depend on their network cabling systems for most of their routine business transactions. If fire occurs and even one metre of cabling is destroyed, it could cost the company millions of dollars each day their systems remain inoperative. These are problems that businessmen do not want to face and one reason why it is necessary to protect sensitive, strategically important cables against fire risk. The Promat Technical Department should be consulted to determine the required board thickness and construction details.

Riser Pipes (Singapore only)

The Fire Safety Bureau of Singapore requires that piping for a rising main is adequately protected to prevent collapse and reduction of water pressure at the point of water egress in the event of a fire. In addition, fire will heat up the water conveyed through the piping system. It is conceivable that water in the pipe could reach a stage of boiling. This would result in additional pressure being placed upon the pipe system as water will expand considerably (1:1700) as it turns to steam. This will result in premature failure of the pipes and joints transporting the water, leading to a loss of pressure and consequential inability to fight or extinguish the fire.

Therefore it is required that rising main piping is adequately protected to:

- Prevent collapse of the piping system,
- Maintain the fire integrity and insulation of the compartment wall or floor where the piping penetrates,
- Prevent water passing through the piping system from reaching its boiling temperature. The temperature at any point on the pipe external surface, measured on the fire-exposed side, must not exceed 75°C above the initial temperature for at least the first 30 minutes of exposure to fire.

The fire resistance test procedure is described in FSB/PSB/001/00 dated 8 November 2000.

General E&M Services Enclosure (Integrity & Insulation)

PS





PROMATECT®-S enclosures provide protection against fire to general building services in accordance with the relevant criteria of BS476: Part 20.

PROMATECT®-S systems are suitable for providing protection to services even under extremely aggressive environments.

The PROMATECT[®]-S systems described below ensure integrity and insulation of fire compartments. If the services are required to continue functioning in the event of fire, please consult the Promat Technical Department.

The maximum permissible dimensions for enclosures described below are 3000mm x 500mm for up to 240 minutes fire resistance.

System Specification

Promat

General E&M services enclosures are to be constructed using PROMATECT[®]-S cement-steel composite boards all in accordance with the Architectural Specification in the manufacturer's handbook. Relevant constructions are to be selected according to the required FRL of 120 or 240 minutes of the selected elements. All printed installation details are to be followed to ensure approval to BS476: Part 20. All work to be certified by installer in an approved manner.

General E&M Services Enclosure (Integrity Only)

PS





PROMATECT®-S enclosures provide protection against fire to general building services in accordance with the relevant criteria of BS476: Part 20.

PROMATECT®-S systems are suitable for providing protection to services even under extremely aggressive environments.

The PROMATECT[®]-S systems described below ensure integrity of fire compartments. If the services are required to continue functioning in the event of fire, please consult the Promat Technical Department.

The maximum permissible dimensions for enclosures described below are 6000mm x 2000mm for up to 240 minutes fire resistance.

System Specification

Promat

General E&M services enclosures are to be constructed using PROMATECT[®]-S cement-steel composite boards all in accordance with the Architectural Specification in the manufacturer's handbook. Relevant constructions are to be selected according to the required FRL of 120 or 240 minutes of the selected elements. All printed installation details are to be followed to ensure approval to BS476: Part 20. All work to be certified by installer in an approved manner.

Promat E&M Services Enclosure Fixing Details

PS

58

⁽⁾ •



The corner junctions of the PROMATECT[®]-S enclosure are reinforced with internal steel angles, minimum size 50mm x 50mm x 3mm. The PROMATECT[®]-S board is connected with M5 Buildex-type steel self-tapping screws at 200mm centres. Transverse board joints are connected in the same manner but with 100mm x 3mm thick steel flat.



Fitting of Mineral Wool

The mineral wool insulation is laid in the soffit boards of the PROMATECT[®]-S. For the top and sides, however, the insulation is fixed in place using nominal M4 self-tapping screws with 25mm-diameter steel washers at nominal 300mm centres in a grid formation. If the insulation is fitted in two or more layers, the joints between the slabs are staggered by at least 300mm between layers. If the insulation is fitted in a single layer, the joints between slabs are sealed and bonded together using VICUBOND[®] WR adhesive.

TECHNICAL DATA

- 1 layer of PROMATECT®-S board For FRL of 120/120/120 6mm thick For FRL of 240/240/240 9.5mm thick
- 2 Steel flat 100mm x 3mm thick at longitudinal joints
- 3 Enclosure hanger support at maximum 2400mm centres, sized according to enclosure weight, size and required fire resistance.
- 4 M5 Teks screws at nominal 200mm centres
- 5 Services steel hanger, sized according to duct weight, size and required fire-resistance. Maximum spacing is 1900mm centres.
- 6 Steel angle 50mm x 50mm x 3mm thick constructed at corner joints
- 7 Steel cable tray
- 8 General E&M services, e.g. cable trunking, steel pipes etc.
- 9 Mineral wool For FRL of 120/120/120 100mm x 140kg/m³ For FRL of 240/240/240 140mm x 140kg/m³
- **10** PROMASEAL® AN Fire Rated Acrylic Sealant



Building Services & Enclosure Support

The hangers used to support the building services enclosure must have tensile and bending stresses not exceeding 10N/mm² and 6N/mm² for fire ratings of up to 120 and 240 minutes respectively. If these stress levels are exceeded, the size of the hanger members must be increased. Alternatively, the spacing of the hangers can be reduced. The maximum spacing of the hangers is 1800mm centres.

The fixings used to fasten the threaded hanger rods to concrete soffits must be all-steel expanding anchors with a penetration into the concrete of at least 40mm for 120 minutes fire resistance and 60mm for 240 minutes fire resistance. The anchors must match the size of the threaded rods and be of sufficient strength to support the weight of the enclosure. Anchors must be fitted in accordance with the manufacturer's specification. When the hanger rods are suspended from protected structural steel beams, the rods must be protected for at least 300mm from the beams with the same levels of protection as the structural beams.

If the building service being encased is a plastic pipe, external hangers and angles will be required to independently support the enclosure.

Internal Cross Section Dimension

The maximum approved internal dimension of the enclosure is 3000mm wide x 500mm high. The width may be increased to 3000mm if an additional rod is fitted at each hanger position at about mid-width. The rod passes through the enclosure and supports the horizontal bearer of the support system beneath the enclosure. The rod also supports the top of the PROMATECT[®]-S enclosure with a nut and large steel washer. The penetrations of the rod through the enclosure are sealed with PROMASEAL[®] AN Acrylic Sealant.

Wall Penetrations

Where the enclosure passes through a fire compartment wall, the penetration must be properly constructed and sealed. Angles $50\text{mm} \times 50\text{mm} \times 3\text{mm}$ are fixed to the top and sides of the enclosure and should be set in a position central to the thickness of the compartment wall. The gap between the exterior surface of the enclosure and the perimeter of the wall aperture should be filted either side and over the angles using 140kg/m^3 mineral wool slabs friction fitted. The aperture is then covered by a PROMATECT®-S cover plate which should extend from the surface of the enclosure and overlap the wall aperture by a minimum of 100mm. The PROMATECT®-S cover plate should be fixed to the wall using all-steel anchors at nominal 500mm centres.



1, 2 & 3-sided Enclosure

3-sided, 2-sided and 1-sided enclosures are constructed in the same way as 4-sided enclosures. The PROMATECT®-S board is connected to the masonry/concrete wall or concrete floor soffit using the same steel angle and screws to the board and M12 all steel expansion bolts, at 500mm maximum centres into the substrate. The bolts must have a minimum penetration into the wall of floor of 60mm. The services are independently supported.







From top: 3-sided, 2-sided and 1-sided E&M services enclosures using PROMATECT^o-S boards.





Architectural Specification

Following is the standard Architectural Specification for general building services enclosure system using PROMATECT[®]-S. The designer must determine the suitability of the design to the application and requirements before undertaking or constructing any works relating to the specifications and where in doubt should obtain the advice of a suitably qualified engineer.

External & Internal Fire

Up to 240 minutes fire rating, integrity and where pertinent insulation in accordance with the criteria of AS1530: Part 4: 2005 and BS476: Part 20: 1987.

Supporting Structure

Care should be taken that any structural element by which the enclosure system is supported, e.g. a beam, floor or wall, has at least equivalent fire resistance.

Lining Boards

Single-layer 6mm/9.5mm^(*) PROMATECT[®]-S cement/steel composite boards as manufactured by Promat International (Asia Pacific) Ltd.

Type of Fixing

The services will be suspended with hanger rods with hanger diameter sized to limit stress, = $10N/mm^2$ and = $6N/mm^2$ for 2-hour and 4-hour fire exposure respectively. Distance between the hangers should not be more than 1800mm centres, depending on the system specification. Mild steel frame made of steel angles, minimum size 50mm x 50mm of thickness 3mm or 5mm, depending on the system specification, are used at the corners of the enclosure. $100mm \times 3mm$ thick steel flats are positioned such that they coincide with the transverse joints of the boards. The steel framework may be mechanically connected or welded together at all junctions.

PROMATECT[®]-S boards will be screw-fixed to the frame with 35mm x 5.5mm Teks screws at 200mm centres. Mineral wool in accordance with the system specification will be tightly filled around the existing services, i.e. between the gap of boards and the services. External hangers to support the enclosure with hanger diameter sized to limit stress, = 10N/mm² and = 6N/mm² for 2-hour and 4-hour fire exposure respectively are located at not more than 2400mm centres.

Tests & Standards

The complete system along with the material and framing is tested and/or assessed to meet the requirements of BS476: Part 20.

NOTES:

- (*) delete as appropriate.
- Perimeter gaps will be filled with fire resistant PROMASEAL® AN Acrylic Sealant.



For latest information of the Promat Asia Pacific organisation, please refer to <u>www.promat-ap.com</u>

ASIA PACIFIC HEADQUARTERS

Promat International (Asia Pacific) Ltd. Unit 19-02-01, Level 2 PNB Damansara No.19 Lorong Dungun, Damansara Heights 50490 Kuala Lumpur MALAYSIA Tel: +60 (3) 2095 5111 Fax: +60 (3) 2095 6111 Email: info@promat-ap.com

AUSTRALIA

Promat Australia Pty. Ltd.

1 Scotland Road Mile End South, SA 5031 Tel: 1800 PROMAT Fax: +61 (8) 8352 1014 Email: mail@promat.com.au

New South Wales Office

Promat Australia Pty. Ltd. Unit 1, 175 Briens Road Northmead, NSW 2152 Tel: 1800 PROMAT Fax: +61 (2) 9630 0258 Email: mail@promat.com.au

Victoria Office

Promat Australia Pty. Ltd. 3/273 Williamstown Road Port Melbourne, VIC 3207 Tel: 1800 PROMAT Fax: +61 (3) 9645 3844 Email: mail@promat.com.au

CHINA

 Promat China Ltd.

 Room 503, Block B, Qi Lin Plaza

 13-35 Pan Fu Road

 510180 Guangzhou

 Tel:
 +86 (20) 8136 1167

 Fax:
 +86 (20) 8136 1372

 Email:
 info@promat.com.cn

Beijing Office Promat North China (Division of Promat China Ltd.) Room 1507 Building 5, SOHO Xiandaicheng No.88 Jianguo Road, Chaoyang District 100022 Beijing

Tel: +86 (10) 8589 1254 Fax: +86 (10) 8589 2904 Email: info@promat.com.cn

HONG KONG

Promat International (Asia Pacific) Ltd.

Room 1010, C.C. Wu Building 302-308 Hennessy Road Wanchai Tel: +852 2836 3692 Fax: +852 2834 4313 Email: apromath@promat.com.hk

For Promat International groups worldwide: www.promat-international.com

1. This document is produced on the basis of information and experience available at the time of preparation. Promat is constantly reviewing and updating all of its test data and reserves the right to change products and specifications without notice.

Promat is not responsible if recipients of fire test reports, assessments or literature incorrectly interpret said contents and use products based on those interpretations.

INDIA

Promat International (Asia Pacific) Ltd. (India Representative Office) 610-611, Ansal Imperial Tower C-Block, Community Centre Naraina Vihar, Naraina 110028 New Delhi Tel: +91 (11) 2577 8413 (general) +91 (99) 6705 0813 (west area) +91 (99) 8994 0505 (south area) Fax: +91 (11) 2577 8414 Email: info-india@promat-asia.com

MALAYSIA

Promat (Malaysia) Sdn. Bhd.

Unit 19-02-01, Level 2 PNB Damansara No.19 Lorong Dungun, Damansara Heights 50490 Kuala Lumpur Tel: +60 (3) 2095 8555 Fax: +60 (3) 2095 2111 Email: info@promat.com.my

SINGAPORE

Promat Building System Pte. Ltd.

10 Science Park Road, #03-14 The Alpha, Singapore Science Park II Singapore 117684 Tel: +65 6776 7635 Fax: +65 6776 7624 Email: info@promat.com.sg

VIETNAM

Promat International (Asia Pacific) Ltd. (Vietnam Representative Office) Room 606 Giay Viet Plaza 180-182 Ly Chinh Thang Street Ward 9, District 3, Hochiminh City Tel/Fax:+84 (8) 3931 5964 (south area) Tel/Fax:+84 (4) 3565 8677 (north area) Hotline:+84 904 055 055 Email: info@promat-asia.com trangoc@promat-asia.com

Your local Promat supplier

